



AE-PCPCOLD is a high solids, concentrated, tint system specially formulated for AE-P100COLD. AE-PCPCOLD is formulated with high quality, ultra fine particle pigments that easily disperse in AE-P100COLD. AE-PCPCOLD is used to obtain a solid base color in AE-P100COLD.

Specifications / Compliances





KEY FEATURES & TYPICAL BENEFITS

- 14 brilliant standard colors to choose from. *Includes black & white
- Effective for creating a base color in the Chip System.
- Easily disperses into AE-P100COLD.
- Use only in AE-P100COLD.

Typical Properties & Technical Information	
PROPERTY	VALUE
Solids/Active Content, Percentage by weight	Concentrated
Pot Life	See AE-P100COLD Tech Data
Dry Time - Tack Free	See AE-P100COLD Tech Data
Dry Time - Foot Traffic	See AE-P100COLD Tech Data
Dry Time - Heavy Traffic	See AE-P100COLD Tech Data
Re-Coat Time Window	See AE-P100COLD Tech Data
Application Temperature	50° F - 80° F
VOC (Volatile Organic Compound) Content	N/A
Appearance - Dry	Tinted and Medium/High Gloss

Information above is based on lab temperatures of 70° - 72° F at 50% RH. Using this product outside these conditions may affect the accuracy of the information above. Always test prior to use!

ALWAYS REFER TO SDS & READ FULL TECH DATA SHEET AND WARRANTY INFORMATION PRIOR TO USE.



RECOMMENDED APPLICATIONS

- Garages
- Basements
- Automotive Shops
- Many other interior concrete surfaces where an extended open time, solid color primer is needed.



APPLICATION INSTRUCTIONS

SURFACE PREP: The concrete surface must be deemed mechanically and structurally sound, completely clean, and dry. To achieve desired results, a mechanical grinding method should be performed with a 30 grit or coarser diamond to insure flatness of the substrate, to remove surface impurities, and to profile the surface of the floor to a CSP-2, as recommended by the ICRI Technical Guideline No. 03732.

Substrate and air temperature must be no less than 50°F and not exceed 80°F. If applied outside these limits the sealer may not achieve adequate film formation and may have excessive air entrapment, bubbles, blushing or hazing. Note that in direct sunlight, substrate temperature can exceed 150° F which can cause extreme bubbling issues.

MIXING: Mix one quart into two gallons of AE-P100COLD Part A for 1-2 minutes using a squirrel mixer prior to blending Part A and Part B. Allow any foam to settle prior to use. Material may separate during long term storage. Re-mix as needed.

USAGE RATE: Solid Opaque Finish: 32 ounces (1 quart) per 3 gallon kit *Usage rates are suggested amounts only! Test prior to use.

APPLICATION INSTRUCTIONS: Application should be completed by rolling or a squeegee and back roll using a 3/8" synthetic nap, phenolic core roller, or a lambs wool cover for pigmented, stained floors, or media coats. It is recommended to use only 18" wide squeegees and rollers. If considering using airless application method, consult the manufacturer prior to application. Please note that the use of pump-up style spray bottle may create visible bubbles, blisters, and pinholes and is not recommended.

Refer to AE-P100COLD's Technical Data and SDS prior to use!

FOR PERSONAL PROTECTION USE GLOVES, GOGGLES, AND RESPIRATORS.

CAUTION: Do not add too much color! Apply a test area prior to job application for desired appearance. Over pigmenting may cause color float or streaking, especially in the darker colors! Do not allow to puddle! The average usage is 1 quart (32 oz.) per 3 gallons of material for most opaque applications. For lighter colors it may take more and darker colors may take less depending on the application.

Use AE-PCPCOLD only with AE-P100COLD!

PLEASE NOTE: It is always recommended to test the product in a small, inconspicuous area (on the same concrete substrate) for desired results prior to application. Coverage rates may vary for all coatings and substrates depending on porosity, density, texture etc. When applying, do not exceed 400 sq. ft. per gallon. Applying too thin of a coating may cause inadequate film formation or performance expectations may be limited. DO NOT USE ON BRICK.

PLEASE NOTE: Applying material outside the suggested parameters may result in product failure. It is always recommended to test the product in a small, inconspicuous area (on the same concrete substrate) for desired results prior to application. Coverage rates may vary for all coatings and substrates depending on porosity, density, texture etc. When applying, adhere to suggested coverage rates. Applying too thin of a coating may cause inadequate film formation, limited performance expectations and/or undesirable finish. Applying too thick may result to bubbling, hazing, etc. DO NOT USE ON BRICK.

COF WARNING: OSHA and the American Disabilities Act (ADA) have now set enforceable standards for slip-resistance on pedestrian surfaces. The current coefficient of friction required by ADA is .6 on level surfaces and .8 on ramps. American Epoxy Flooring Services recommends the use of slip-resistant aggregate in all coatings or flooring systems that may be exposed to wet, oily or greasy conditions. It is the contractor and end users' responsibility to provide a flooring system that meets current safety standards. American Epoxy Flooring Services nor its sales agents will be responsible for injury incurred in a slip and fall accident. For interior floors subjected only to foot traffic, Wax may be used as an acceptable slip-resistant coating as it meets requirements for ASTM D2047.





PRECAUTIONS AND LIMITATIONS

- This product will not freeze during storage, however, allow temperature to rise to 50°F prior to application.
- All HVAC ventilation ducts should be somehow blocked prior to application so solvent fumes are not distributed.
- Use proper ventilation while applying and for hours after application to ensure fumes are removed.
- It is not recommended to apply product over carpet, tile, or other types of floor adhesives.
- This product performs best when applied as one or two medium-light coats, not one heavy coat.
- This product is not resistant to brake fluid, gasoline, and many similar products.
- It is not recommended to thin product. Improper thinning may cause sealer to delaminate in a short time frame.
- This product may darken the surface of many new and existing concrete slabs. Test prior to use.
- Solvent vapors are heavier than air and may travel along the ground or may be moved by ventilation and ignited by pilot lights, other flames, sparks, heaters, smoking, electric motors, static discharge, or other ignition source locations distant from material handling point.

CLEAN-UP: Use xylene. Dispose of containers in accordance with local, state and federal regulations.

PRODUCT REMOVAL: Refer to AE-P100COLD technical data sheet.

SHELF LIFE: Up to one year from manufacture date in its original, unopened container stored at room temperature.

PACKAGING: Available in 1 quart containers.

Always read all technical information, label and SDS prior to use. This information can be found online or by calling customer service at the number below.

American Epoxy Flooring Services warrants our products to be of good quality, free of defects and will conform with our published specifications in force on the date of acceptance of the order. As the exclusive remedy for breach of this warranty, we will replace defective materials. Ninety days after American Epoxy Flooring Services has shipped the products, all our warranty and other duties with respect to the quality of the materials delivered shall conclusively be presumed to have been satisfied, all liability therefore terminates, and no action for breach of any said duties may thereafter be commenced. No warranty is expressed or implied as to the length of life of this product, or merchantability or fitness. Liability, if any, is limited to the purchase price of the material. Under no circumstances will American Epoxy Flooring Services be liable for a consequential damage to anyone in excess of the purchase price of the products.